

High Performance Cement Grinding Aid for Vertical Roller Mills

Description

NIROGRIND AD4022 is a liquid, ready-to-use, high performance cement grinding aid, specially designed for cement grinding in Vertical Roller Mills, to increase the powder flowability of the finished cement without reduction of the stability of the material bed, by reducing the polarity of the cleaved surface and the attraction forces between cement particles.

It also significantly reduces the mill vibrations, water injection at constant vibrations, pack set tendencies and increases productivity with improved quality cement.

NIROGRIND AD4022 is effective in both open circuit and closed-circuit cement mills.

It is compatible with all types of cement and complies with ASTM C465-99 as a nonharmful processing additive.

Uses

- ✓ Ordinary Portland cement
- ✓ Blended cement with limestone, fly ash or slag.

The special characteristics of NIROGRIND AD4022 effectively activate the hydration process between cement particles and the non-reactive or reactive fillers.

For additional information on NIROGRIND AD4022 and its use in developing special performance characteristics, contact your local Nirman Chemicals Limited sales field representative.

Advantages

- ✓ Reduces mill vibrations (30% to 50% reduction).
- ✓ Reduces water injection (up to 50%) at constant vibrations due to better stabilization and regulation of the bed thickness.
- ✓ Lower water addition to cement often reduces setting time and has positive effects on strengths.
- ✓ Mineral additive rates can be increased.
- ✓ Increase of early (24 and 48 hours) mechanical strengths of cements.

- ✓ Increases mill production (10% to 20%) depending on the efficiency of the equipment and the characteristics of the material to be ground.
- ✓ Reduces grinding energy costs.
- ✓ Improves physical properties of the ground material.
- ✓ Improves performance in both closed and open circuit systems at equal specific surface area or equal sieve residues.
- ✓ Powder flow characteristics are improved before, during and after storage.
- ✓ Pack set tendencies and coating are substantially reduced.
- ✓ The risk of false set is reduced due to lower grinding temperature.
- ✓ Cement particle size distribution is improved resulting in more thorough hydration.
- ✓ Reduces plastic shrinkage (Initial set).

Working Mechanisms

NIROGRIND AD4022 accelerates the formation of Ettringite by accelerating the hydration process of C_3A and A_4AF as well as its transformation into monosulphoaluminate to improve cement early strength.

Another function of NIROGRIND AD4022 is to partially neutralize the charges present on the surface of cement particles, which are developed during milling, hence reduce the surface free energy of the material being ground. The additive molecules get adsorbed on the surface of the cement particles by weak electrostatic force, favoring the repulsion and/or steric hindrance between particles, which not allow the agglomeration of cement particles and as a result grinding efficiency improves. Similarly, the 'coating' effect is partially or totally avoided, enhancing other issues such as handling and storage conditions (boosting the 'pack set') or the separator efficiency, also improve the life of grinding media.

Characteristics

Form	: Liquid
Colour	: Brownish

Relative Density : 1.18 ± 0.02 at 25°C
 pH : >6
 Alkali content : < 10% Na₂O equivalent

Dosage

Optimum dosage of NIROGRIND AD4022 should be determined by site trials only.

However, as a guide, typical dosage rates will vary from 0.02% - 0.06% by weight of cement for Types I & II cements and 0.03% - 0.07% by weight of cement for Type III cements.

Higher dosage might be needed for higher percentage of clinker replacement or less reactive cement

Direction for use

NIROGRIND AD4022 can be added at the clinker feed conveyer belt or directly into the cement mill's first compartment. A proper dosing pump is required to ensure the correct dosage into the cement for obtaining the optimum performance. Our technical supports are available to provide assistance in the use of NIROGRIND AD4022 with the manual, automatic or computerized dispensing system.

Technical support

NIRMAN CHEMICALS provides technical advisory services for on-site assistance and guidance on mix design, optimum dosage evaluation of trials.

Packaging

NIROGRIND AD4022 is supplied in 250 kg drums, 1100 kg IBC or in bulk on request.

Storage and Shelf life

NIROGRIND AD4022 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature.

Shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.

For specific storage advice consult our local NIRMAN CHEMICALS representative.

Safety precautions

NIROGRIND AD4022 does not fall into the hazard classifications. However, it should not be swallowed or allowed to come into contact with the skin and eyes. Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with the eyes it shall be rinsed immediately with plenty of water and medical advice sought immediately. If swallowed, medical attention shall be sought immediately - Vomiting should not be induced.

Fire

NIROGRIND AD4022 is water based and non-flammable.

Cleaning of Tools

Clean all tools and application equipment with water immediately

Note

All Technical Data Sheets are updated on regular basis; it is the user's responsibility, to obtain the most recent issue.

Field services where provided, does not constitute supervisory responsibility, for additional information contact our local NIRMAN CHEMICALS representative.

Disclaimer

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labor involved in the application are beyond our control.



NIRMAN CHEMICALS

CORPORATE ADDRESS:

Flat: B4, House: 28/B, Road: 3, Banani DOHS, Dhaka - 1213.

FACTORY ADDRESS:

Norsinghar Chor (Amtola Bazar), Noakanda, Polash, Narsingdi.

HOTLINE: +88 02 983 2929

W: www.nirmanchemicals.com

E: contact@nirmanchemicals.com

FB: fb.com/nirmanchemicals

COMPLETE CONSTRUCTION CAR 2[2]



AN ISO CERTIFIED COMPANY