

SUPER PLASTICIZING ADMIXTURE FOR CONCRETE AND MORTAR – SPECIALLY DEVELOPED FOR REAL ESTATE

Description

NIROCRETE SUPREME is a super plasticizing admixture for Concrete and Mortar based on specially selected polymers. The product has been developed specially for **Real Estate** for the applications on site concrete. NIROCRETE SUPREME allows considerable reduction of mixing water while maintaining control on extend of set retardation thus improve the compressive strength of concrete and mortar without increasing the cement content.

It makes concrete more impermeable and durable.

Uses

- ✓ on site concrete
- ✓ Long-distance transporting
- ✓ Pumped concrete
- ✓ High workability without segregation or bleeding
- ✓ Mixes requiring >15% water reductions

Advantages

- ✓ Dose sensitivity is very less
- ✓ Suitable for lower to medium grade of concrete
- ✓ Resistance to segregation and bleeding even at high workability at high dose
- ✓ At high dosage it does not have high retardation effect
- ✓ Low viscosity suitable for pumping of different grades of concrete to higher floors
- ✓ Can also be utilized for high strength and high-performance concrete
- ✓ Reduced water content for a given workability
- ✓ Higher ultimate strengths
- ✓ Increased ease in finishing concrete

Reaction Mechanisms

NIROCRETE SUPREME has a different chemical structure from the traditional superplasticisers. It is a unique combination of the latest generation superplasticisers, based on a polycarboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the beginning of the mixing process it initiates the same electrostatic dispersion mechanism as the traditional superplasticisers, but the side chains linked to the polymer backbone generates a steric hindrance. NIROCRETE SUPREME considerably reduces the water demand in flowable concrete and improves the workability retention, as it having

both the Electrostatic repulsion and Steric hindrance.

which greatly stabilizes the cement particles' ability to separate and disperse.

NIROCRETE SUPREME considerably reduces the water demand in flowable concrete and improves the workability retention, as it having both the Electrostatic repulsion and Steric hindrance.

Characteristics

Form	: Liquid
Colour	: Brownish
Relative Density	: 1.05 ± 0.02 at 25°C
pH	: Min. 6
Chloride ion content	: Nil (As per BS 5075 Part I)

Standard Compliance

NIROCRETE SUPREME complies with BS:5075 and ASTM-C-494 Type 'A, D & G' depending on dosage.

Dosage

Optimum dosage of NIROCRETE SUPREME should be determined by site trials only using the materials and conditions that will be experienced in use. However, as a guide, a dosage range of 0.4 to 1.5% on cementitious material is recommended. Dosages outside of the recommended range may be required. In such cases, contact our local representative.

Effects of under and overdosing

Under dosages may cause lack of workability and over dosage may cause bleeding & segregation, extension of setting time and increase in air entrainment.

Direction for use

NIROCRETE SUPREME is a ready-to-use liquid admixture.

For maximum dispersion throughout the mix, measured quantity of NIROCRETE SUPREME should be added into the mixer at the same time as the mixing water. The plasticizing effect and water reduction will be higher when the admixture will be added to the damp concrete by adding 60 to 80% of the mixing water in it.

The addition of NIROCRETE SUPREME to dry aggregate or cement is not recommended.

To impart higher workability to concrete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix the concrete for 5 minutes at 10 rpm to produce a fully homogenous mix, before discharge.

Technical support

NIRMAN CHEMICALS provides technical advisory services for on-site assistance and guidance on mix design, optimum dosage evaluation of trials.

Compatibility

NIROCRETE SUPREME can be used with all types of cements except high alumina cement. It is compatible with ligno-sulphonates and carboxylic acid based plasticiser and retarders and also with most type of air entertainers, accelerators, viscosity modifying agent, extended set-control admixtures, corrosion inhibitors, and shrinkage reducers. Site trials should be carried out to optimize dosages.

It is not compatible with Melamine or Naphthalene based admixtures and should not be used in conjunction in the same mix.

Durability

Reduction in W/C ratio enables increase in density and impermeability thus enhancing durability of concrete.

Corrosion

It neither initiates nor promotes corrosion as it does not content any harmful chemicals. Rather it reduces the risk of corrosion of reinforcement or other embedment, as it has high water reduction power to produce a dense impermeable concrete.

Packaging

NIROCRETE SUPREME is supplied in 20 kg, 225 kg drums or in bulk on request.

Storage and Shelf life

NIROCRETE SUPREME must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature.

Shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.

For specific storage advice consult our local NIRMAN CHEMICALS representative.

Safety precautions

NIROCRETE SUPREME does not fall into the hazard classifications. However, it should not be swallowed or allowed to come into contact with the skin and eyes. Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with the eyes it shall be rinsed immediately with plenty of water and medical advice sought immediately. If swallowed, medical attention shall be sought immediately - Vomiting should not be induced.

Fire

NIROCRETE SUPREME is water based and non-flammable.

Cleaning of Tools

Clean all tools and application equipment with water immediately

Note

All Technical Data Sheets are updated on regular basis; it is the user's responsibility, to obtain the most recent issue.

Field services where provided, does not constitute supervisory responsibility, for additional information contact our local NIRMAN CHEMICALS representative.

Disclaimer

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labor involved in the application are beyond our control.



COMPLETE CONSTRUCTION CARE^{2[2]}

CORPORATE ADDRESS:

Flat: B4, House: 28/B, Road: 3, Banani DOHS, Dhaka - 1213.

FACTORY ADDRESS:

Narsinghar Chor (Amtola Bazar), Noakanda, Polash, Narsingdi.

HOTLINE: +88 02 983 2929

W: www.nirmanchemicals.com

E: contact@nirmanchemicals.com

FB: fb.com/nirmanchemicals

AN ISO CERTIFIED COMPANY

