NIRMAN CHEMICALS

NIRODENSE LS

TECHNICAL DATA SHEET

PREMIUM LITHIUM SILICATE-BASED LIQUID CONCRETE FLOOR DENSIFIER & HARDENER

Description

NIRODENSE LS is a premium lithium silicate-based concrete densifier that penetrates concrete capillaries and reacts with free lime to form insoluble calcium silicate hydrate (C–S–H), increasing surface density and hardness while retaining breathability.

Ideal for machine-trowelled, burnished and polished concrete, it improves abrasion resistance and durability, reduces surface dusting not caused by underlying defects, and helps minimise long-term maintenance.

Compatible with concrete grinding and polishing systems, NIRODENSE LS enhances polished colour, gloss and clarity. It dries with minimal visible change, while additional gloss can be achieved through machine application and resin-pad buffing.

Uses

NIRODENSE LS is recommended as a densifier and hardener for machine trowelled concrete surfaces. It can also be used on other cementitious surfaces where densifying and hardening benefits are desired. It is recommended as a polishing aid for burnished or polished concrete surfaces. NIRODENSE LS is ideal for sealing commercial and residential concrete floors such as workshop floors, warehouse floors, automotive garage floors, retail store floors, pole barn and shed floors, basement floors, garage floors, and other machine trowelled, burnished, or polished concrete surfaces. Compatible with most glues, mastics, and topical coatings.

Advantages

- Enhances Polished Concrete Appearance: Helps enhance colour depth, gloss and visual clarity when used as part of a suitable concrete grinding and polishing system.
- Improves Surface Hardness: Reacts with available cementitious compounds to help densify and harden the concrete surface.
- Reduces Dusting: Helps minimise surface dusting caused by weak or friable concrete.
- Improves Abrasion Resistance: Helps improve resistance to wear from normal pedestrian and industrial traffic.
- Supports Concrete Polishing: Helps prepare suitable concrete surfaces for grinding and polishing operations.
- Reduces Surface Porosity: Helps reduce surface porosity and liquid absorption, depending on the substrate and application.
- Non-Film-Forming Treatment: Densifies the concrete without relying on a conventional surface film when properly applied.
- Water-Based Formulation: Suitable for professional concrete-floor treatment applications.

Typical Properties

Aspect	: Clear to turbid liquid
Relative Density	: 1.12 ± 0.02 at 25°C
pH	: Min. 6
Chloride ion content	: Nil (As per BS 5075 Part I)
VOC Content	: 0 g/L
Freeze Point	: 0° C

Directions for use:

Surface preparation

Substrates to be sealed must be a minimum of 28 days old and/ or be fully cured, which should be clean and porous enough to allow penetration into the substrate. Surfaces should be clean and free of surface laitance, dust, dirt, debris, mildew, oil, grease, previous sealers, curing agents, paint or other surface coatings, and other contaminants. If acid or other cleaning compound is used for cleaning or etching the surface, neutralize the surface completely before application of NIRODENSE LS.

Application Method

1. Apply NIRODENSE LS uniformly using a low-pressure sprayer, microfiber applicator or suitable floor-treatment equipment.
2. Spread the material evenly to achieve uniform surface contact.
3. Work the liquid into the concrete using suitable equipment where required.
4. Maintain the recommended wet contact time established during application trials.
5. Prevent uncontrolled pooling and remove excess liquid before it dries into a residue.
6. Allow the surface to dry and cure according to site conditions and the validated application procedure.
7. For polished concrete, follow the applicable

COMPLETE CONSTRUCTION CARE

grinding and polishing sequence.

Important: Do not allow silicate residue to dry as a heavy surface deposit. Actual contact time and residue-removal requirements must be established through field trials.
If a coarse non-slip surface is desired, start curing without any more finishing operations.

Drying and Return to Service

Drying time depends on ambient temperature, humidity, ventilation, concrete porosity and application rate.
Allow the treated surface to dry adequately before foot traffic. Heavy traffic, polishing and subsequent coatings should only proceed when the application-specific requirements have been met.
Final drying and return-to-service times are to be established by testing.

Limitations

- ✓ Not a substitute for a waterproofing membrane.
- ✓ Does not correct structurally weak, delaminated or severely deteriorated concrete.
- ✓ Does not replace a dedicated chemical-resistant or oil-resistant coating.
- ✓ Results depend on the availability of reactive calcium-bearing compounds in the substrate.
- ✓ Excess application may cause surface residue, whitening or other appearance defects.
- ✓ Compatibility with subsequent coatings, sealers and polishing systems must be confirmed before use.
- ✓ Clean the tools and equipment with water before the paste sticking to them hardens

Technical support

NIRMAN CHEMICALS provides technical advisory services for on-site assistance and guidance on mix design and applications.

Coverage

6-8 M^2/Kg for machine troweled and smooth surfaces.
Note: Coverage rates are approximate and for estimating purposes only. Application rate based upon porosity and absorption. Always test absorption prior to application.

Packaging

NIRODENSE LS is supplied in 20 kg, 250 kg drums or in bulk on request.

Storage and Shelf life

Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment.
Shelf life is 24 months when stored as above.
Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult our local NIRMAN CHEMICALS representative.

Safety precautions

NIRODENSE LS does not fall into the hazard classifications. However, it should not be swallowed or allowed to come into contact with the skin and eyes.
Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with the eyes, it shall be rinsed immediately with plenty of water and medical advice sought immediately. If swallowed, medical attention shall be sought immediately - Vomiting should not be induced.

Fire

NIRODENSE LS is non-flammable.

Cleaning of Tools

Clean all tools and application equipment with water immediately

Note All Technical Data Sheets are updated on regular basis; it is the user's responsibility, to obtain the most recent issue. Field services where provided, does not constitute supervisory responsibility, for additional information contact our local NIRMAN CHEMICALS representative.

Disclaimer

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the

CORPORATE ADDRESS:
Flat: B4, House: 28/B, Road: 3, Banani DOHS, Dhaka - 1213.
FACTORY ADDRESS:
Norsinghar Chor (Amtola Bazar), Noakanda, Polash, Narsingdi.
HOTLINE: +88 02 983 2929 **E:** contact@nirmanchemicals.com
W: www.nirmanchemicals.com **FB:** fb.com/nirmanchemicals

AN *ISO* CERTIFIED COMPANY
ISO 9001:2015 Quality Assurance Certification
ISO 14001:2015 Environmental Management Certification
ISO 45001:2018 Health & Safety Certification

competence of any labor involved in the application are beyond our control.

CORPORATE ADDRESS:
Flat: B4, House: 28/B, Road: 3, Banani DOHS, Dhaka - 1213.
FACTORY ADDRESS:
Norsinghar Chor (Amtola Bazar), Noakanda, Polash, Narsingdi.
HOTLINE: +88 02 983 2929 **E:** contact@nirmanchemicals.com
W: www.nirmanchemicals.com **FB:** fb.com/nirmanchemicals

AN *ISO* CERTIFIED COMPANY

ISO 9001:2015 Quality Assurance Certification
ISO 14001:2015 Environmental Management Certification
ISO 45001:2018 Health & Safety Certification